

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08F 14/18	A1	(11) International Publication Number: WO 00/32655 (43) International Publication Date: 8 June 2000 (08.06.00)
(21) International Application Number: PCT/US99/28000 (22) International Filing Date: 29 November 1999 (29.11.99) (30) Priority Data: 60/110,282 30 November 1998 (30.11.98) US 09/450,106 29 November 1999 (29.11.99) US (71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors: WILLIAM, Brown, Farnham; 123 Dewberry Drive, Hockessin, DE 19707 (US). FEIRING, Andrew, Edward; 7 Buckridge Drive, Wilmington, DE 19807 (US). LINDNER, Patrick, Edward; 44 Scenic Hills Drive, Parkersburg, WV 26101 (US). (74) Agent: STEINBERG, Thomas, W.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		(81) Designated States: CN, JP, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: FLUOROMONOMER POLYMERIZATION (57) Abstract Chain transfer agents that are chlorine-free and liquid under polymerization conditions, useful for fluoromonomer polymerization, have the following formula: R^1-O-R^2 . They are superior to common chain transfer agents such as chloroform in being safer and environmentally benign. They are also superior to gaseous chain transfer agents such as ethane because they do not enter the fluoromonomer gas recycle streams and so do not complicate the analysis and purification of those streams.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

TITLE


Fluoromonomer Polymerization

FIELD OF THE INVENTION

5 This invention is in the field of fluoromonomer polymerization using chain transfer agents.

BACKGROUND OF THE INVENTION

10 In its simplest form, free-radical polymerization begins with the reaction of a free radical, generated by an initiator, with an olefin molecule to form a new free radical. This adds in turn to another olefin molecule in a polymerization cycle which continues until the growing radical chain is
15 terminated by coupling or disproportionation with another radical chain, or by reaction with an initiator-generated radical. The rate of termination compared with the rate of polymerization affects the molecular weight and molecular weight distribution of
20 the polymer, both critical properties. Because these termination mechanisms do not always give desirable molecular weights or molecular weight distributions and sometimes produce polymer molecules with unstable endgroups or bonds, chain transfer agents are often
25 included in polymerization recipes. See for example U. S. Patent nos. 3,636,926 and 5,700,889. Chain transfer agents are molecules with labile atoms, often hydrogen. They give up the labile atom to a growing polymer chain, terminating it. In the process the chain
30 transfer agent is converted to a free radical which initiates a new polymer chain by reacting with an olefin molecule, starting a new polymerization cycle. Chloroform is an example:



Though effective in fluoromonomer polymerization, chloroform has undesirable health and environmental effects. Hydrocarbons, such as ethane, are also used as chain transfer agents, and are free of the problems of chloroform. However, ethane is a gas. Many fluoromonomers are also gases, and polymerizations often include the recycling of monomers. The presence of chain transfer agents such as ethane in monomer recycle streams presents problems of analysis and purification that increase costs and the probability of contamination. Liquid hydrocarbons are unsuitable because to achieve low enough volatility so that they do not have a significant concentration in the gas phase, their molecular weights must be high. Fluoropolymers made with high molecular weight hydrocarbon chain transfer agents would have hydrocarbon end groups that would affect their properties and stability.

New chain transfer agents are needed that do not contain chlorine, are liquid at room temperature, and do not significantly affect the character of the polymer being made.

SUMMARY OF THE INVENTION

The present invention provides a chain transfer agent that is chlorine-free, liquid at room temperature, and similar in chemical composition to fluoropolymers made with them, that the fluoropolymer properties are not adversely affected. Thus the invention is a process comprising the polymerizing of fluoromonomer in the presence of initiator and chain transfer agent, said chain transfer agent having the formula

35



wherein R^1 is a straight chain or branched saturated hydrocarbon group of 1 to 6 carbon atoms with the proviso that there is at least one hydrogen atom attached to the carbon next to oxygen, and R^2 is a
 5 straight chain or branched fluorocarbon group or hydrofluorocarbon group of formula $C_aH_bF_c$ wherein a is 2 to 6, b is 0 to 2a-1 and c is 2 to 2a+1 with the proviso that $b+c = 2a+1$.

Another aspect of the invention is polymer
 10 containing endgroups characteristic of chain transfer agent having the formula (1)



wherein R^1 and R^2 are as defined above.

15

DETAILED DESCRIPTION

Olefins are molecules containing a carbon-carbon double bond ($>C=C<$). The vinyl group ($CH_2=CH-$) is a member of the class of olefins. "Fluoromonomers"
 20 is used in this application to mean olefins that can be free-radically polymerized and that contain at least one fluorine atom, fluoroalkyl group, or fluoroalkoxy group attached to the vinyl group that undergoes polymerization. Useful fluoromonomers include, but are
 25 not limited to, vinyl fluoride; vinylidene fluoride; trifluoroethylene; chlorotrifluoroethylene (CTFE); 1,2-difluoroethylene; tetrafluoroethylene (TFE); hexafluoropropylene (HFP); perfluoro(alkyl vinyl ethers) such as perfluoro(methyl vinyl ether) (PMVE),
 30 perfluoro(ethyl vinyl ether) (PEVE), and perfluoro(propyl vinyl ether) (PPVE); perfluoro(1,3-dioxole); perfluoro(2,2-dimethyl-1,3-dioxole) (PDD); $CF_2=CFOCF_2CF(CF_3)OCF_2CF_2X$ wherein X is SO_2F , CO_2H , CO_2CH_3 , CH_2OH , CH_2OCN or CH_2OPO_3H ; $CF_2=CFOCF_2CF_2SO_2F$;
 35 $F(CF_2)_nCH_2OCF=CF_2$ wherein n is 1, 2, 3, 4, or 5; $R_4CH_2OCF=CF_2$ wherein R_4 is hydrogen or $F(CF_2)_m-$ and m is 1, 2 or 3; and $R_5OCF=CH_2$ wherein R_5 is $F(CF_2)_z-$ and z is 1, 2, 3, or 4; perfluorobutyl ethylene (PFBE);

3,3,3-trifluoropropene and 2-trifluoromethyl-3,3,3-trifluoro-1-propene. Preferred fluoromonomers include 2-trifluoromethyl-3,3,3-trifluoro-1-propene, PFBE, vinyl fluoride, vinylidene fluoride, TFE, HFP, PMVE, 5 PEVE, PPVE, CTFE, and PDD.

The fluoromonomer may be polymerized alone to form a homopolymer if the fluoromonomer can be homopolymerized, or may be polymerized with one or more other fluoromonomers or other monomers, such as 10 hydrocarbon monomers that are not fluoromonomers, to form a copolymer. If a copolymer is to be formed, the monomers chosen must be able to copolymerize. Fluorine-free monomers that copolymerize with some combinations of fluoromonomers include propylene and 15 ethylene. Examples of useful homopolymers from fluoropolymers include polytetrafluoroethylene (PTFE) and polyvinylidene fluoride. Also usually classed with homopolymer PTFE are the modified PTFE polymers containing fluoromonomers other than TFE in such minor 20 amounts that the modified polymers retain the non-melt-fabricable character of PTFE. Examples of useful copolymers include the copolymers of TFE with HFP and/or perfluoro(alkyl vinyl ethers) such as PPVE or PEVE, copolymers of TFE with PMVE, copolymers of TFE 25 with PDD, and copolymers of TFE or CTFE with ethylene. Further examples include the copolymers of vinylidene fluoride with HFP, or with HFP and TFE. As implied above, copolymers may contain additional monomers beyond those named. TFE/ethylene copolymers, for 30 example, are most useful if they include additional monomers that introduce bulky side groups such as PFBE, HFP, PPVE or 2-trifluoromethyl-3,3,3-trifluoro-1-propene, and elastomeric polymers frequently include low concentrations of cure site moieties derived from a 35 cure site monomer.

The polymers of this invention include TFE and CTFE homopolymers; TFE or CTFE polymerized with one or more other fluoromonomers described above such that

said other fluoromonomers are <1% by weight of the total polymer (wt.%); TFE or CTFE polymerized with 1 to 99 wt.% of one or more other fluoromonomers, preferably 1 to 50 wt.% of one or more other fluoromonomers, more preferably 1 to 20 wt.% of one or more other fluoromonomers, and most preferably 1 to 10 wt.% of one or more other fluoromonomers. In all cases, the wt.% values refer to the amount of comonomer incorporated in the polymer.

10 The TFE homopolymers of this invention are not melt fabricable. The copolymers of this invention are melt processible with melt viscosities, determined as described below, of up to 10^6 Pa•s, preferably in the range 10^2 to 10^6 Pa•s, and most preferably in the range 15 10^3 to 10^5 Pa•s. Such fluoropolymers can be glassy, plastic, or elastomeric. They can be amorphous or partially crystalline, melt-fabricable or non-melt-fabricable. The fluoropolymers made by the process of this invention are normally solid at 15°-20°C and can 20 have any molecular weight (MW) suitable for the intended use. Generally, the weight average MW is at least 50,000 and can range up to much higher values, such as 1,000,000 and even higher.

The identity and proportion in the polymer of 25 units derived from other monomers, fluorinated and fluorine-free, can have wide ranges depending on the physical, chemical, or electrical properties sought. Thus, the polymers of this invention can be plastic or elastomeric, generally according to the identity and 30 proportion of units derived from monomers making up the major part of the polymer composition, as known in the art.

Polymers of this invention can be prepared by any of the known processes for making fluoropolymers. 35 Such processes can be conducted, for example, in an aqueous or non-aqueous liquid medium, the latter including fluorocarbon and chlorofluorocarbon solvents and carbon dioxide, or in mixed media, i.e., hybrid

processes, as well known in the art. The olefin, initiator, and chain transfer agent of formula (1) are added to the polymerization medium, i.e. the polymerization medium is not the chain transfer agent.

5 The presence of the chain transfer agent in the polymerization reaction is in addition to the presence of a polymerization medium. The polymerization medium will normally constitute at least 40 wt.% of the polymerization system after polymerization is

10 completed. As is also well known in the art, dispersion or suspension processes can be employed, and polymerization can be conducted in a batch, semi-batch, or continuous process.

Initiators commonly employed in aqueous

15 polymerization of TFE copolymers are water-soluble free-radical initiators such as ammonium persulfate (APS), potassium persulfate (KPS), or disuccinic acid peroxide, or redox systems such as those based on potassium permanganate (KMnO_4), or a perfluoroalkyl

20 sulfinate salt plus an oxidizing agent. Such initiators can be used in the process of this invention. Preferred initiators include APS, KPS, and KMnO_4 .

Initiators for nonaqueous polymerization or

25 polymerization in the solvent phase of a suspension polymerization include perfluoropropionyl peroxide (3P) and $(\text{CF}_3\text{CF}_2\text{CF}_2\text{OCF}(\text{CF}_3)\text{COO}-)_2$ (hexafluoropropylene oxide dimer peroxide also known as HFPO dimer peroxide).


Surfactants for aqueous polymerizations include

30 ammonium fluoroalkanoates such as ammonium perfluorooctanoate and 3,3,4,4,5,5,6,6,7,7,8,8,8,-tridecafluorooctylsulfonic acid, partially neutralized with ammonia.

35 Syntheses of Chain Transfer Agents

The chain transfer agents useful in the present invention may be prepared by several processes known to those skilled in the art. A preferred process involves


the addition of alcohols to fluorine-containing olefins as illustrated in equation 1. This process is normally carried out in the presence of a catalytic amount of a base such as an alkali metal hydroxide or the alkali metal salt of the alcohol R^1OH . This process is discussed by M. Hudlicky in "Chemistry of Organic Fluorine Compounds", 2nd edition, Ellis Horwood, Chichester, UK, 1976, pages 285 to 290 and 407 to 410 and by L. G. Sprague in "Chemistry of Organic Fluorine Compounds II", M. Hudlicky and A. E. Pavlath, editors, American Chemical Society, Washington, DC. 1995, pages 729 to 731.



15

Synthesis of the compound $CH_3OCF_2CF_2H$ from methanol and tetrafluoroethylene by this process is disclosed in U. S. no. patent 3,609,196. Synthesis of the compound $CH_3CH_2OCF_2CF_2H$ from ethanol and tetrafluoroethylene is disclosed in European Patent Application EP 694523.

Chain transfer agents of formula (1) may also be obtained by reaction of fluorine-containing ketones or acid fluorides with an alkali metal fluoride and an alkylating agent of formula R^1-L as illustrated in equation 2.



wherein R^1 has the meaning defined above, L is a leaving group, and M is an alkali metal cation. A leaving group is an atom or group of atoms which, when attached to a primary or secondary carbon atom, is readily displaced by a nucleophile. Typical leaving groups include chloride, bromide, iodide, alkyl sulfates, alkyl sulfonates, arylsulfonates and trifluoromethanesulfonate anions. This process is discussed by A. E. Feiring in "Chemistry of Organic

Fluorine Compounds II", M. Hudlicky and A. E. Pavlath, editors, American Chemical Society, Washington, DC. 1995, page 82.

Chain transfer agent of formula (1) may also be
5 obtained by reaction of a fluorine containing alcohol R^2OH with an alkylating agent of formula R^1-L . In one example, reaction of 1,1,1,3,3,3-hexafluoro-2-propanol with dimethyl sulfate in the presence of aqueous sodium hydroxide affords a partially fluorinated ether with
10 the formula $(CF_3)_2CHOCH_3$, as disclosed in U. S. Patent no. 3,346,448.

Two of the chain transfer agents in the class described by the formula (1), in which $R^2 =$ perfluoroalkyl, are available commercially from 3M
15 Corporation: Methoxy nonafluorobutane ($CH_3-O-C_4F_9$), which is sold as HFE-7100 hydrofluoroether; and ethoxy nonafluorobutane ($CH_3CH_2-O-C_4F_9$), which is sold as HFE-7200 hydrofluoroether. The use of HFE-7100 and HFE-7200 as polymerization media is disclosed in "Research
20 Disclosures", January 1998, p.81, #40576. Similar hydrofluoroethers are also disclosed as polymerization media in U. S. Patent no. 5,182,342.

Amounts of chain transfer agent used in typical polymerizations range from 0.1-100 parts per thousand
25 (ppt), preferably 1-100 ppt, and more preferably 1-50 ppt. The parts per thousand are based on the total weight of the monomer or monomers fed to the polymerization reaction, i.e. the weight initially charged and subsequently fed to the polymerization
30 vessel in the course of the polymerization. The chain transfer agent may be added during the initial charging of ingredients before polymerization is begun, or it may be added continuously or in portions during polymerization, or during the initial charging and in
35 the course of the polymerization.

Of the chain transfer agents of formula (1), preferred chain transfer agents are those in which a is 2 or 3 and b is 1 or 2. It is believed that the

- presence of one or two hydrogen atoms in the group R^2 increases solubility of the chain transfer agent in water, and therefore chain transfer agents with $b = 1$ or 2 may be especially preferred in aqueous polymerizations. More preferred are those in which R^1 has at least two carbon atoms at least one of which is a secondary carbon atom. A secondary carbon atom is one that is bonded to two hydrogen atoms and to two other atoms.
- 10 Polymers of this invention contain polymer chains that are terminated with endgroups characteristic of the chain transfer agents. These endgroups are similar in formula to the chain transfer agent used, the principal difference being that the polymer chain is
- 15 bonded to a carbon atom of the chain transfer agent that formerly was bonded to a hydrogen.

TEST METHODS

- Relative polymer molecular weights were determined
- 20 by melt index measurements in which the amount of polymer which flows through a given orifice at a specified time and temperature and under a specific weight is determined. Thus, a higher melt index number corresponds to a lower molecular weight. Melt index
- 25 tests were run using a Slocumb Model F extrusion plastometer with a 316 stainless steel die 0.947 cm in diameter and with an orifice 0.318 cm long and 0.0794 cm in diameter. The plastometer was heated to 372°C. After loading about 2 g of polymer, reinserting the
- 30 piston and waiting 5 minutes for thermal equilibration, the piston was loaded with dead weight so that the piston and dead weight together totaled 5, 10 or 15 kg. The time required for all or part of the sample to be extruded was measured. The weight of the polymer
- 35 extruded in one minute is measured. Generally, two or three measurements are averaged and multiplied by 10. The result is reported as melt index in units of g/10 minutes. In some cases in which polymer of very low

molecular weight was formed, all or part of the polymer sample extruded from the plastometer during the 5 minute equilibration time. In these cases, the melt index is reported as "high".

5 The number of unstable end groups was determined by infrared spectroscopy on thin polymer films which were compacted by pressing at room temperature. Peak intensities at about 1775, 1815, 1795 and 1660 cm^{-1} were used to determine -COOH (dimer), -COOH (monomer),
10 -CF=CF₂ and -COO⁻K⁺ concentrations, respectively. Intensity of a band at about 2365 cm^{-1} was used to correct absorptions for film thickness. The total of -COOH, -CF=CF₂ and -COO⁻K⁺ groups is reported as number of ends per 10⁶ polymeric carbon atoms (10⁶ C).

15 Polymer compositions were determined by ¹⁹F NMR spectroscopy on melted polymer samples at about 300 to 320°C. The amount of hexafluoropropylene incorporated was determined by integration of a signal at about -71 ppm (CF₃) versus the total of CF₂ absorptions in the
20 region -105 to -130 ppm. The amount of perfluoro (ethyl vinyl ether) incorporated was similarly determined by integration of its CF₃ peak at about -88 ppm.

25 Example 1 and Comparative Examples A and B
 Copolymerization of Tetrafluoroethylene (TFE) and
 Hexafluoropropylene (HFP)

 A 4-L horizontal autoclave with mechanical agitator was purged with nitrogen and charged with 2-L
30 of distilled water, 4.48 g of ammonium perfluorooctanoate, and the chain transfer agent, if used. The amount of chain transfer agent is reported in Table 1 as parts per thousand parts of the monomers initially charged to the autoclave plus the monomers
35 fed to the autoclave in the course of the polymerization. For convenience, Table 4 gives the volumes of chain transfer agent used in each experiment. The reactor was purged with a mixture of 70

wt.% HFP and 30 wt.% TFE while the contents were heated to 103 °C and agitated at 90 rpm. The reactor was pressured to 4.5 MPa with the above gas mixture. A solution of 4 g of ammonium persulfate initiator in 1-L of water was injected at a rate of 6 mL/minute for 12 minutes. Then a solution of 7 g of potassium persulfate initiator in 1-L of water was injected at the rate of 1 mL/minute and pressure in the reactor was maintained at 4.5 MPa by the addition of TFE. Reaction was continued until 840 g of TFE had been injected. The time from first injection of the ammonium persulfate initiator to complete addition of the tetrafluoroethylene is reported as the run time. The initiator and TFE feeds were stopped, the reactor was allowed to cool and vented to atmospheric pressure. The reactor contents were discharged, frozen in dry ice, thawed and filtered. The solid polymer was stirred with about 2-L of distilled water at about 80 °C, filtered and dried in a vacuum oven overnight at about 120 °C under a flow of nitrogen. Results are reported in Table 1. For these polymers, a melt viscosity as a measure of molecular weight was calculated from the formula

$$\text{melt viscosity} = (10.68) * (\text{piston} + \text{dead weight}) / (\text{grams of polymer extruded in 1 min})$$

A higher melt viscosity indicates a higher molecular weight.

30

Table 1. Copolymerizations of TFE and HFP

#	Chain Transfer Agent		Run Time (min)	Melt Viscosity	Ends /10 ⁶ C	Composition
	Formula	Amount (ppt* of monomer)		X 10 ⁴ (poise)		Wt.% HFP
1	CH ₃ OCF ₂ CF ₂ H	9.4	104	12.9	259	8.81
A	None	0	107	33.9	217	10.0
B	CHCl ₃	unknown	141	3.1	303	9.6

* ppt = parts per thousand

Examples 2 - 15 and Comparative Examples C - G

5 Terpolymerization of Tetrafluoroethylene (TFE),
Hexafluoropropylene (HFP) and Perfluoro(ethyl vinyl
ether) (PEVE)

A 4-L horizontal autoclave with mechanical
 agitator was purged with nitrogen and charged with 2.2-
 10 L of distilled water and 26 g of 20 wt.% solution of
 ammonium perfluorooctanoate in water. The reactor was
 purged with a mixture containing 61 wt.% HFP and 39
 wt.% TFE while the contents were heated to 103 °C and
 agitated at 190 rpm. The reactor was pressured to 4.14
 15 MPa with the above gas mixture. Perfluoro (ethyl vinyl
 ether) (12 mL) and the chain transfer agent, if used,
 were then pumped into the reactor. The amount of chain
 transfer agent is reported in Table 2 as parts per
 thousand parts of the monomers initially charged to the
 20 autoclave plus the monomers fed to the autoclave in the
 course of the polymerization. For convenience, Table 4
 gives the volumes of chain transfer agent used in each
 experiment. A solution of 5.6 g of potassium
 persulfate initiator in 1-L of water was pumped into
 25 the reactor at a rate of 10 mL/min until 25 mL had been
 injected. Then this initiator solution was pumped into
 the reactor at a rate of 0.6 mL/min and PEVE was pumped
 in at a rate of 0.1 mL/min. The reactor pressure was
 maintained at 4.14 MPa by the addition of TFE until 840

g of TFE had been added. The time from first injection of the potassium persulfate initiator until complete addition of the tetrafluoroethylene is reported as the run time. The initiator and TFE feeds were stopped,
5 the reactor was allow to cool and vented to atmospheric pressure. The reactor contents were discharged, frozen in dry ice, thawed and filtered. The solid polymer was stirred with about 2-L of distilled water at about 80 °C, filtered and dried in a vacuum oven overnight at
10 about 120 °C under a flow of nitrogen. Results are reported in Table 2. All melt index measurements in Table 2 were made with the 5 kg weight, so melt index is reported without conversion to molecular weight.

Table 2. Terpolymerizations of TFE, HFP and PEVE

#	Chain Transfer Agent		Run Time (min)	Melt Index (g/10 min)	Ends /10 ⁶ C	Composition wt. %	
	Formula	Amount (ppt* of monomer)				HFP	PEVE
2	CH ₃ CH ₂ OCF ₂ CF ₂ H	5	164	high	290	5.7	2.7
3	CH ₃ CH ₂ OCF ₂ CF ₂ H	2.5	149	114	289	6.3	2.2
4	CH ₃ CH ₂ OC ₄ F ₉	12	113	67.9	233	6.1	1.8
5	CH ₃ CH ₂ OC ₄ F ₉	6	115	34.8	256	6.5	2.1
6	CH ₃ OCF ₂ CF ₂ H	32	167	high		5.8	2.7
7	CH ₃ OCF ₂ CF ₂ H	21	153	102	275	6.0	2.9
8	CH ₃ OCF ₂ CF ₂ H	21	143	99.8	282	6.1	2.6
9	CH ₃ OCF ₂ CF ₂ H	10.5	149	41.3		6.0	2.6
10	CH ₃ OCF ₂ CF ₂ H	10.5	163	46.0		6.0	2.4
11	CH ₃ OCF ₂ CF ₂ H	5.2	158	27.0		6.0	2.5
12	CH ₃ OC ₄ F ₉	39	103	19.1	238	6.5	2.1
13	CH ₃ OC ₄ F ₉	39	116	20.8	236	5.7	2.3
14	CH ₃ OCH(CF ₃) ₂	8	115	30.8		6.2	2.2
15	CH ₃ OCH(CF ₃) ₂	17	149	132		6.5	2.5
C	none	0	125	8.9	239	6.3	2.4
D	none	0	105	3.2	220	6.6	1.7
E	none	0	119	8.8	249	6.5	2.3
F	none	0	108	5.0	229	6.7	2.0
G	none	0	111	6.7	240	6.9	2.0

ppt = parts per thousand

5 Examples 16 - 22 and Comparative Examples H - I
Terpolymerization of Tetrafluoroethylene (TFE),
Hexafluoropropylene (HFP) and Perfluoro(ethyl vinyl
ether) (PEVE)

10 The procedures of examples 2 to 15 were followed
except that 15 g of a 23 wt.% solution of
3,3,4,4,5,5,6,6,7,7,8,8,8-tridecafluorooctylsulfonic
acid, partially neutralized with ammonia, was used in

place of the ammonium perfluorooctanoate. Results are reported in Table 3. All melt index measurements in Table 3 were made with the 5 kg weight, so melt index is reported without conversion to molecular weight.

5

Table 3. Terpolymerizations of TFE, HFP and PEVE

#	Chain Transfer Agent		Run Time (min)	Melt Index (g/10 min)	Ends /10 ⁶ C	Composition wt. %	
	Formula	Amount (ppt* of monomer)				HFP	PEVE
16	CH ₃ OCF ₂ CF ₂ H	10.4	135	31.9	229	5.8	1.7
17	CH ₃ OCF ₂ CF ₂ H	5.2	128	21.8	287	6.1	1.8
18	CH ₃ OC ₄ F ₉	25	116	13.7	219	6.1	2.0
19	CH ₃ CH ₂ OCF ₂ CF ₂ H	5	> 180	high	314	6.0	3.2
20	CH ₃ CH ₂ OCF ₂ CF ₂ H	1	169	32.7	282	6.4	2.3
21	CH ₃ CH ₂ OC ₄ F ₉	12	> 180	high	277	6.3	2.6
22	CH ₃ CH ₂ OC ₄ F ₉	6	162	67.3	262	5.8	2.5
H	none	0	129	10.8	303	6.4	2.0
I	none	0	132	9.1	245	5.9	2.4

ppt = parts per thousand

Table 4. Volumes of Chain Transfer Agent Used in Examples

Example Number	Chain Transfer Agent (mL)	Example Number	Chain Transfer Agent (mL)
1	10	15	15
A	0	C	0
B	1.6	D	0
2	5	E	0
3	2.5	F	0
4	10	G	0
5	5	16	10
6	30	17	5
7	20	18	20
8	20	19	5
9	10	20	1
10	10	21	10
11	5	22	5
12	30	H	0
13	30	I	0
14	7	23	8.8

5 Example 23: Initiation with Perfluorobutanesulfinate Salt

Copolymerization of Tetrafluoroethylene (TFE) and Hexafluoropropylene (HFP)

10 A 4-L horizontal autoclave with mechanical agitator was purged with nitrogen and charged with 2-L of distilled water, 4.48 g of ammonium perfluorooctanoate and the chain transfer agent, $\text{CH}_3\text{OCF}_2\text{CF}_2\text{H}$ (11.0 g). The chain transfer agent was 9.6 ppt of the total of the monomers charged and fed to the

15 autoclave in this polymerization. The reactor was purged with a mixture of 70 wt.% HFP and 30 wt.% TFE while the contents were heated to 103 °C and agitated at 90 rpm. The reactor was pressured to 4.5 MPa with

the above gas mixture. This charge amounted to 144 g TFE and 336 g of HFP. A solution of 4 g of ammonium persulfate initiator in 1-L of water was injected at a rate of 6 mL/minute for 3 minutes. Then a solution of ammonium perfluorobutanesulfinate (15 g/liter) and a solution of sodium bromate (10.4 g/liter) were added independently, each at 0.6 mL/min for the remainder of the batch. Pressure in the reactor was maintained at 4.5 MPa by the addition of TFE which was continued in this example until 660 g of TFE had been injected (run time = 163 min). The initiator and TFE feeds were stopped, the reactor was allow to cool and was then vented to atmospheric pressure. The reactor contents were discharged, frozen in dry ice, thawed and filtered. The solid polymer was isolated as described in Example 1. Copolymer composition consisted of 8.9 wt.% HFP, 91.1 wt.% TFE, with melt viscosity determined as 3.5×10^4 poise. Comparative runs using similar molar quantities of sulfinate salt initiator but with no chain transfer agent afforded copolymer with higher melt viscosity, illustrating the effectiveness of chain transfer agent $\text{CH}_3\text{OCF}_2\text{CF}_2\text{H}$ with alternate initiators.

Examples 24 - 28 and Comparative Example J :
Terpolymerization of Tetrafluoroethylene (TFE),
Hexafluoropropylene (HFP) and Perfluoro(ethyl vinyl
ether) (PEVE) in 10-gallon autoclave.

A 10-gallon horizontal autoclave with mechanical agitator was purged with nitrogen and charged with 48 lb. (22 kg) of distilled water and 200 grams of a 20 wt% solution of ammonium perfluorooctanoate in water. The reactor was purged with TFE while the contents were heated to 65°C and agitated at 50 RPM. A vacuum was pulled on the reactor, and then the chain transfer agent was drawn in through a charge pot in the amount reported in Table 5 as parts per thousand parts of the

monomers initially charged to the autoclave plus the monomers fed to the autoclave in the course of the polymerization. The reactor temperature was raised to 103°C and agitated at 50 RPM. Perfluoro(ethyl vinyl ether) (130 mL) was then pumped into the reactor. The autoclave was then pressured to 380 psig (2.7 MPa) with HFP and then to 635 psig (4.48 MPa) with TFE. A 5.4 g/L of potassium persulfate initiator was pumped into the reactor at a rate of 50 mL/min until 190 mL was added. The initiator pump rate was then reduced to 4.4 mL/min for the remainder of the reaction period. Perfluoro(ethyl vinyl ether) was also added at a rate of 1.0 mL/min for the remainder of the batch. Pressure was maintained between 550-650 psig (3.9-4.6 MPa) by feeding TFE until a total of 18.0 lb. (8.16 kg) of TFE were fed. TFE and initiator feeds were stopped and the reactor was cooled to 90°C before slowly venting the contents to atmospheric pressure. The reactor contents were discharged. Polymer isolation was accomplished by shear coagulation, followed by 24 hours of drying at 150°C in an open air oven. Results are reported in Table 5.

Table 5. Terpolymerization with TFE, HFP, PEVE in 10-L autoclave.


Example #	Formula	Amount		Melt Index (g/10 min.)	Ends/ 10 ⁶ C	Composition Wt %	
		mL	ppt *			HFP	PEVE
24	CH ₃ CH ₂ OCF ₂ CF ₂ H	22	2.9	10.4	119	5.1	1.8
25	CH ₃ CH ₂ OCF ₂ CF ₂ H	45	5.9	19.9	92	5.4	1.9
26	CH ₃ OCH(CF ₃) ₂	22	3.0	4.3	188	6.4	1.8
27	CH ₃ OCH(CF ₃) ₂	52	7.1	7.9	128	7.0	1.9
28	Chloroform	30	3.9	11.2	114	5.1	1.6
J	none	0	0	1.3	108	6.7	2.0

* ppt - parts per thousand of monomers

The examples show that the chlorine-free, liquid chain transfer agents of this invention are effective in controlling the molecular weights of fluoropolymers, including TFE/HFP and TFE/HFP/PPVE, in polymerizations using different initiators and surfactants.

WHAT IS CLAIMED IS:

1. A process comprising polymerizing a fluoromonomer comprising an olefin which contains at least one fluorine atom on an olefinic carbon in the presence of
5 a polymerization initiator and chain transfer agent, said chain transfer agent having the formula



- 10 where R^1 is a straight chain or branched saturated hydrocarbon group of 1 to 6 carbon atoms with the proviso that there is at least one hydrogen atom attached to the carbon next to oxygen, and R^2 is a straight chain or branched fluorocarbon group or
15 hydrofluorocarbon group of formula $C_aH_bF_c$ wherein a is 2 to 6, b is 0 to $2a-1$ and c is 2 to $2a+1$ with the proviso that $b+c = 2a+1$.

2. A polymer made by the process of claim 1.

20

3. The process of claim 1 wherein hydrocarbon monomer is present.

4. The process of claim 1 wherein said polymerization
25 is carried out in a polymerization medium to which said olefin, initiator, and chain transfer agent are added.


5. The process of claim 1 wherein R^2 is CF_2CF_2H or $CH(CF_3)_2$.

30

6. The process of claim 5 wherein R^1 is methyl or ethyl.

7. The process of claim 1 wherein the amount of chain
35 transfer agent present is 0.1-100 parts per thousand based on the total weight of monomer feed to said process.

8. The process of claim 1 wherein said polymerization is carried out in an aqueous medium.
9. Polymer containing endgroups characteristic of chain transfer agent having the formula



- wherein R^1 is a straight chain or branched saturated hydrocarbon group of 1 to 6 carbon atoms with the proviso that there is at least one hydrogen atom attached to the carbon next to oxygen, and R^2 is a straight chain or branched fluorocarbon group or hydrofluorocarbon group of formula $C_aH_bF_c$ wherein a is 2 to 6, b is 0 to $2a-1$ and c is 2 to $2a+1$ with the proviso that $b+c = 2a+1$.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/28000

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C08F14/18

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 617 058 A (AUSIMONT SPA) 28 September 1994 (1994-09-28) abstract; claims 1-3 ---	1-9
A	US 5 182 342 A (FEIRING ANDREW E ET AL) 26 January 1993 (1993-01-26) cited in the application example 11 ---	1-7,9
A	GRENFELL M W: "HYDROFLUOROETHERS AS FLUOROMONOMER REACTION MEDIA" RESEARCH DISCLOSURE, GB, INDUSTRIAL OPPORTUNITIES LTD. HAVANT, no. 405, 1 January 1998 (1998-01-01), pages 81-82, XP000772402 ISSN: 0374-4353 cited in the application the whole document -----	1-7,9



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

3 May 2000

Date of mailing of the international search report

11/05/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Friederich, P

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/28000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0617058 A	28-09-1994	IT MI930551 A	23-09-1994
		AT 158310 T	15-10-1997
		CA 2119411 A	24-09-1994
		DE 69405618 D	23-10-1997
		DE 69405618 T	23-04-1998
		ES 2108313 T	16-12-1997
		JP 7090008 A	04-04-1995
		US 5516863 A	14-05-1996
US 5182342 A	26-01-1993	DE 69304515 D	10-10-1996
		DE 69304515 T	20-02-1997
		EP 0628059 A	14-12-1994
		JP 7504224 T	11-05-1995
		WO 9317053 A	02-09-1993

THIS PAGE BLANK (USPTO)